U GROUP SRL
Via Borgomanero n° 1
28040 Paruzzaro (NO)

LEGAL DATA:
C.F e Reg.Imp.Novara: 02041920030
CCIAA Novara REA: 211799
P.IVA: IT02041920030
Codice Export: No015724
Cap.Soc.: 119.000 Iv

CONTACTS:
WEBSITE: www.u-power.it/en
EMAIL: info@u-power.it
TEL: +39 0322 53 94 01
FAX: +39 0322 23 00 01

REV. 11/11/2024

DATA SHEET

UF20234 JAMES S3S FO SR
Natural Confort 11 Mondopoint®
AirToe Aluminium
SHOE TYPE "A"
SIZE RANGE 38-48 (UK: 5-13)
Size tested: 42 - WEIGHT Kg 1,2125

PRODUCT PICTURE



RANGES

FLAT OUT

TECHNOLOGIES

Save&Flex plus · wingtex · PUTR PU GRIP · PU Tek PLUS HYPERTEX technology · Natural CONFORT 11 · Airtoe ALUMINIUM · U-POWER ORIGINAL · Secosol

DESCRIPTION

Safety shoes low, light and comfortable U-Power of the Flat Out range, High abrasion resistant, PUTEK® PLUS, water repellent and breathable, aluminum toecap, anti-puncture, anti-slip and PU / PUTR GRIP sole.

TECHNICAL SPECIFICATIONS

TECHNICAL SPECIFICATIONS	EN ISO STANDARD	VALUE
SAFETY TOE CAP "AirToe Aluminium"	**20345:2022**	**RESULT**
Impact resistance. Free heights after collision mm	≥ 14	20,0
Compressive strength. Free heights after compr. mm	≥ 14	20,5
INSOLE "Save & Flex PLUS® , pierce resistant “non metal”"		
Puncture resistance N	≥ 1100	Compliant
ELECTRICAL RESISTANCE CATEGORY	$< 10^9$ Ω	N.A.
UPPER DYNAMIC WATERPROOFING AFTER 60'		
Water absorption after 60'	≤ 30%	5,5
Water transmitted after 60'	≤ 0,2 gr	0
Permeability to water vapor mg/(cm^2 h)	≥ 0,8	114,8
Permeability coefficient mg/cm^2	≥ 15	918,8
VAMP LINING		
Permeability to water vapor mg/(cm^2 h)	≥ 2	19,0
Permeability coefficient mg/cm^2	≥ 20	153
Resistance to abrasion - DRY cycles	25.600 cycles	Compliant
Resistance to abrasion - WET cycles	12.800 cycles	Compliant
INSOLE		
Abrasion resistance	≥ 400 cycles	No damage
SOLE WEAR		
Abrasion resistance (volume loss) mm^3	≤ 150	61
Bending resistance mm	≤ 4	2,2
Resistance to sole / midsole detachment N/mm	≥ 3	4,7
Hydrocarbons resistance (% volume variation)	≤ 12	2,5
Heel energy absorption J	≥ 20	36
SLIP RESISTANCE		
Slip resistance on ceramic with NaLS (forward heel 7°)	≥ 0,31	0,46
Slip resistance on ceramic with NaLS (backward forepart 7°)	≥ 0,36	0,45
SR-Slip resistance on ceramic with glycerin (forward heel 7°)	≥ 0,19	0,21
SR-Slip resistance on ceramic with glycerin (backward forepart 7°)	≥ 0,22	0,29a